

Appl. No. 10/530,096  
Amdt. Dated August 30, 2006  
Reply to Office Action of June 1, 2006

RECEIVED  
CENTRAL FAX CENTER  
AUG 30 2006

**Amendment to the Claims**

This listing will replace all prior versions, and listings, of the claims in the application:

**Listing of Claims:**

Claim 1 (Cancelled)

Claim 2 (Currently amended): A sealing material in combination with an according to Claim 1, for use in sealing automobile engine cam cover wherein the sealing material seals the automobile engine cam cover and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components.  
eovers.

Claim 3 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, where a liquid acrylic polymer having a number average molecular weight  $M_n$  of 500 or more and a molecular weight distribution ( $M_w/M_n$ ) of 1.8 or less is used as component (A) of the composition.

Appl. No. 10/530,096  
Amdt. Dated August 30, 2006  
Reply to Office Action of June 1, 2006

Claim 4 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, where the cured product of the composition has a Duro A hardness of 45 or less.

Claim 5 (Currently amended): A sealing material ~~for cam covers~~ according to Claim 2, in combination with a for use in resin-made cam cover covers.

Claim 6 (Previously presented): An automobile engine cam cover sealed by a sealing material for cam covers according to Claim 2.

Claim 7 (Currently amended): A sealing material in combination with an according to Claim 1, for use as a sealing material for automobile engine oil pan wherein the sealing material seals the automobile engine oil pan and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components.  
~~pan.~~

Claim 8 (Currently amended): A sealing material ~~for oil pans~~ according to Claim 7, wherein a liquid acrylic polymer having a number average molecular weight  $M_n$  of 500 or more and a molecular weight distribution ( $M_w/M_n$ ) of 1.8 or less is used as component (A) of the composition.

Appl. No. 10/530,096  
Amdt. Dated August 30, 2006  
Reply to Office Action of June 1, 2006

Claim 9 (Currently amended): A sealing material ~~for oil pans according to Claim 7~~, wherein the cured product of the composition has a Duro A hardness of 45 or less (according to JIS K6253).

Claim 10 (Currently amended): Automobile engine oil ~~pan~~ ~~pans~~ sealed by a sealing material for oil ~~pans which comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components.~~ ~~pans according to Claim 7.~~

Claims 11-14 (Cancelled):

Claim 15 (Currently amended): A sealing material in combination with an according to Claim 1, for use in automobile wire harness wherein the sealing material seals the automobile wire harness and comprises a cured product of a composition comprising (A) an acrylic polymer having at least one alkenyl group capable of undergoing hydrosilylation reaction, (B) a hydrosilyl group-containing compound and (C) a hydrosilylation catalyst as essential components. harnesses.

Claim 16 (Currently amended): A sealing material ~~for automobile wire harnesses~~ according to Claim 15, wherein a liquid acrylic polymer having a number average molecular weight  $M_n$  of 500 or more

Appl. No. 10/530,096  
Amdt. Dated August 30, 2006  
Reply to Office Action of June 1, 2006

and a molecular weight distribution ( $M_w/M_n$ ) of 1.8 or less is used as component (A) of the composition.

Claim 17 (Currently amended): A sealing material for automobile wire harnesses according to Claim 15, wherein the cured product of the composition has a Duro A hardness of 50 or less (according to JIS K6253).

Claim 18 (Currently amended): A sealing material for automobile wire harnesses according to Claim 15, wherein not more than 100 parts by weight of a reinforcing agent or a filler is added to the composition on the basis of 100 parts by weight of sum total of components (A), (B) and (C).

Claim 19 (Original): Automobile wire harnesses sealed by a sealing material for wire harnesses according to Claim 15.

Claims 20-31 (Cancelled)

Claim 32 (Currently amended): A sealing material for automobile wire harnesses according to Claim 17, wherein not more than 100 parts by weight of a reinforcing agent or a filler is added to the composition on the basis of 100 parts by weight of sum total of components (A), (B) and (C).

Appl. No. 10/530,096  
Amdt. Dated August 30, 2006  
Reply to Office Action of June 1, 2006

Claim 33 (Cancelled)